

QUALITY EVALUATION LABORATORY

N 65-19868

FACILITY FORM 602

(ACCESSION NUMBER)

(THRU)

(PAGES)

(CODE)

(NASA CR OR TMX OR AD NUMBER)

(CATEGORY)

14
CR-57420

03

"PREPARED FOR THE NATIONAL AERONAUTICS
AND SPACE ADMINISTRATION, GODDARD SPACE
FLIGHT CENTER, SPACE POWER TECHNOLOGY
BRANCH, GREENBELT, MARYLAND, PURSUANT
TO PURCHASE ORDER NUMBER W11,252B."


NAD CRANE, INDIANA

GPO PRICE \$ _____

OTS PRICE(S) \$ _____

Hard copy (HC) \$1.00

Microfiche (MF) \$0.50



QUALITY EVALUATION LABORATORY
UNITED STATES NAVAL AMMUNITION DEPOT
CRANE, INDIANA

EVALUATION PROGRAM
FOR
SECONDARY SPACECRAFT CELLS

ACCEPTANCE TEST
OF
GULTON INDUSTRIES, INC.
12 AMPERE-HOUR CELLS

QE/C 65-124

16 February 1965

THIS REPORT IS LIMITED TO GOVERNMENT AGENCIES.
OTHER REQUESTS FOR COPIES SHOULD BE MADE TO:
NATIONAL AERONAUTICS AND SPACE ADMINISTRATION
GODDARD SPACE FLIGHT CENTER (CODE 636.2)
GREENBELT, MARYLAND 20771

PREPARED UNDER THE DIRECTION OF

E. C. Bruess

E. C. BRUESS
Manager, Electrochemical
Power Sources Branch

APPROVED BY

E. R. PETTEBONE
COMMANDING OFFICER

V. Yeager
V. YEAGER
By direction

Enclosure (1)

REPORT BRIEFGULTON 12 AMPERE-HOUR NICKEL CADMIUMSECONDARY SPACECRAFT CELLS

- Ref: (a) National Aeronautics and Space Administration Purchase Order Number W11,252B
(b) NASA ltr BRA/VRK/pad of 25 September 1961 w/BUWEPS first end FQ-1;WSK of 2 October 1961 to CO NAD Crane
(c) Preliminary Work Statement for Battery Evaluation Program of 25 August 1961

I. TEST ASSIGNMENT BRIEF.

A. In compliance with references (a) and (b), evaluation of Gulton Industries, Inc. 12 ampere-hour Secondary Spacecraft Cells was begun according to the program outline of reference (c).

B. The object of this evaluation program is to gather specific information concerning secondary spacecraft cells. Information concerning performance characteristics and limitations, including cycle life under various electrical and environmental conditions, will be of interest to power systems designers and users. Cell weaknesses, including causes of failure of present designs, will be of interest to suppliers as a guide to product improvement.

C. Thirty cells were purchased from Gulton Industries, Inc., Metuchen, New Jersey by National Aeronautics and Space Administration (NASA). These cells are rated at 12 ampere hours by the manufacturer and are similar to those used in the OGO satellite program.

II. CONCLUSIONS.

A. From the results of this test, it can be concluded that:

1. The ceramic seals of these cells manufactured by Gulton Industries, Inc., are satisfactory as evidenced by no leakers out of the 30 cells tested.
2. The capacity of the cells was in the acceptable range of 13.6 to 15.5 ampere-hours.

III. RECOMMENDATIONS.

A. It is recommended that these Gulton Industries, Inc. 12 ampere-hour cells be accepted on the basis of the acceptance test results.

D. These cells, rated by the manufacturer at 12.0 ampere-hours, were supplied in a discharged (with shorting wire) condition.

IV. TEST PROCEDURES AND RESULTS.

A. Capacity Test.

1. The capacity test is a determination of the cell capacity at the $c/2$ discharge rate, where c is the manufacturer's rated capacity to a cutoff voltage of 1.00 volt per cell. The discharge was made after a 1-hour open circuit period following the 16-hour charge at the $c/10$ rate. Since one capacity check was submitted by the manufacturer, the second and third capacity checks were made at this activity. The cells were discharged individually but were recharged in series.

2. The cell capacities of the second and third capacity checks, made by this activity, generally were quite similar or slightly lower than those submitted by the manufacturer. The individual cell capacities ranged from 13.6 to 15.5 ampere-hours for an average of 14.3 ampere-hours. The cell capacities are tabulated in Table I. Characteristic 2-hour rate discharge curves are shown in Figure 2.

B. Cell Short Test.

1. The cell short test is a means of detecting slight shorting conditions which may exist because of imperfections in the insulating materials, or damage to element in handling or assembly.

2. Following completion of the third capacity discharge test, each individual cell was loaded with a resistor of value giving a c to $c/5$ discharge rate and allowed to stand 16 hours with the resistor acting as a shorting device. At the end of 16 hours, the resistors were removed and the cells were placed on open circuit stand for 24 hours. Any cell whose voltage did not recover to 1.15 volts or higher was rejected.

3. The open circuit cell voltages, 24 hours after removal of the shorting resistors, ranged from 1.20 to 1.23 volts for an average of 1.22 volts..

4. Of the 31 cells subjected to the cell short test, one was rejected. The voltage values for the 30 accepted cells are shown in Table I.

C. Immersion Seal Test.

1. The immersion seal test is a means of detecting leakage of a seal or weld. The test was performed before and after the over-charge test sequence to determine the presence and cause of leaks.

2. The cells were placed under water in a bell jar container. A vacuum of 20 inches of mercury was held for 3 minutes. Cells discharging a steady stream of bubbles were considered rejects.

3. There were no rejects in the 30 cells subjected to the immersion seal test.

D. Overcharge Test.

1. The overcharge tests were performed to determine the steady state voltage at specified rates. The test specified a series of constant current charges at c/20, c/10 and c/5 rates, for a minimum of 48 hours at each charge rate or until the increase of the "on-charge" voltage was less than 10 millivolts per day.

2. The cells were monitored hourly throughout the test. Charging was to be discontinued on cells which exceeded 1.50 volts while on charge. There was no need to remove any cells from the charging sequence.

3. The steady state voltage and temperature of each cell, taken on the positive terminal, at the end of each 48-hour charge rate test is shown in Table I. Characteristic overcharge voltage curves are shown in Figure 3.

E. Internal Resistance Test.

1. This test was performed to determine the internal resistance of the cell.

2. At the completion of the overcharge test; the cells were returned to the c/20 charging rate and given a short pulse (5-10 seconds) at a rate of c in amperes. The cell voltages, V1, immediately prior to the pulse; and V2, 5 milliseconds after the pulse, were read on a suitable recording instrument. A CEC high speed tape recorder (28.8 inches of tape per second) was used. The internal resistance of the cell in ohms was calculated according to the following formula:

$$R = \frac{V2 - V1}{Ic - Ic/20}$$

V1 and V2 are in volts, Ic and Ic/20 are in amperes.

3. The internal resistance value for each cell is shown in Table I. The values range from 0.87 milliohms to 2.02 milliohms.

TABLE I

CELL NUMBER	WEIGHT (GRAMS)	HEIGHT (INCHES)	LENGTH (INCHES)	WIDTH (INCHES)	CAPACITY TESTS			CELL SHORT TEST	IMMERSION SEAL TEST LEAKAGE	OVERCHARGE c/20 °F	OVERCHARGE c/10 °F	OVERCHARGE c/5 °F	INTERNAL RESISTANCE (MILLIOHMS)	IMMERSION SEAL TEST LEAKAGE
					FIRST BY MANUFACTURER	SECOND BY NAD CRANE	THIRD BY NAD CRANE							
1439	544.5	4.608	0.895	2.99	14.2	13.6	12.6	1.22	NONE	1.41 87	1.44 93	1.44 104	2.02	NONE
1443	541.0	4.600	0.899	2.89	14.2	13.6	12.6	1.22	NONE	1.41 88	1.44 93	1.43 103	0.87	NONE
1445	540.0	4.600	0.890	2.99	14.5	13.7	12.8	1.22	NONE	1.41 88	1.44 92	1.43 103	0.87	NONE
1447	541.0	4.615	0.890	2.99	15.1	14.2	13.4	1.22	NONE	1.41 86	1.44 94	1.43 104	0.87	NONE
1449	539.0	4.625	0.890	2.99	15.0	13.8	12.7	1.23	NONE	1.41 87	1.44 94	1.43 102	0.87	NONE
1450	543.0	4.604	0.896	2.89	15.0	13.9	13.0	1.21	NONE	1.41 86	1.44 93	1.43 104	1.75	NONE
1452	548.0	4.600	0.895	2.99	15.2	14.5	13.6	1.20	NONE	1.41 87	1.44 93	1.43 104	1.75	NONE
1454	541.0	4.591	0.895	2.89	15.0	14.2	13.3	1.21	NONE	1.41 87	1.44 92	1.42 104	1.75	NONE
1455	542.5	4.620	0.888	2.85	15.1	15.0	14.6	1.21	NONE	1.42 88	1.44 94	1.44 102	1.75	NONE
1456	548.5	4.608	0.900	2.89	14.8	13.7	12.8	1.23	NONE	1.41 88	1.44 93	1.43 103	1.75	NONE
1457	543.0	4.625	0.896	2.89	14.9	14.6	14.0	1.22	NONE	1.41 88	1.41 94	1.44 103	1.75	NONE
1458	552.0	4.612	0.892	2.99	15.4	15.5	13.7	1.22	NONE	1.41 87	1.41 92	1.42 103	1.75	NONE
1459	544.5	4.590	0.890	2.89	14.7	14.3	13.8	1.22	NONE	1.41 89	1.41 92	1.43 103	1.75	NONE
1460	546.0	4.612	0.891	2.99	14.6	14.0	13.6	1.22	NONE	1.40 87	1.41 94	1.48 104	1.75	NONE
1461	546.5	4.590	0.896	2.99	15.3	14.7	13.8	1.21	NONE	1.41 87	1.40 93	1.43 104	1.75	NONE

TABLE I (Contd)

CELL NUMBER	WEIGHT (GRAMS)	HEIGHT (INCHES)	LENGTH (INCHES)	WIDTH (INCHES)	CAPACITY TESTS			CELL SHORT TEST	IMMERSION SEAL TEST LEAKAGE	OVERCHARGE c/20 °F	OVERCHARGE c/10 °F	OVERCHARGE c/5 °F	INTERNAL RESISTANCE (MILLIOHMS)	IMMERSION SEAL TEST LEAKAGE			
					FIRST BY MANUFACTURER	SECOND BY NAD CRANE	THIRD BY NAD CRANE										
1462	540.5	4.600	0.894	2.99	15.2	14.5	13.4	1.22	NONE	1.40	89	1.40	93	1.42	102	1.75	NONE
1464	543.0	4.616	0.895	2.99	14.9	14.2	13.8	1.22	NONE	1.41	87	1.41	92	1.43	104	0.87	NONE
1465	544.5	4.603	0.896	2.99	15.4	14.8	14.4	1.21	NONE	1.40	87	1.41	94	1.43	103	1.75	NONE
1466	543.0	4.615	0.893	2.89	15.0	14.5	14.0	1.22	NONE	1.41	89	1.41	93	1.44	104	0.87	NONE
1467	543.5	4.625	0.896	2.99	14.6	13.6	13.3	1.21	NONE	1.41	88	1.42	93	1.42	104	0.87	NONE
1468	542.5	4.625	0.893	2.99	14.2	1.37	12.7	1.22	NONE	1.40	88	1.41	94	1.41	105	1.75	NONE
1469	547.0	4.625	0.893	2.89	15.0	14.2	13.4	1.22	NONE	1.40	87	1.41	94	1.40	106	1.75	NONE
1470	543.5	4.610	0.893	2.99	14.8	14.0	13.4	1.22	NONE	1.40	87	1.41	94	1.40	104	0.87	NONE
1471	543.5	4.590	0.899	2.89	13.9	14.8	14.4	1.21	NONE	1.44	86	1.46	94	1.44	106	1.75	NONE
1473	546.0	4.588	0.900	2.89	14.5	14.4	14.1	1.22	NONE	1.40	88	1.41	94	1.40	106	1.75	NONE
1474	547.0	4.600	0.900	2.89	15.3	14.5	13.3	1.22	NONE	1.42	87	1.44	94	1.42	104	0.87	NONE
1476	543.5	4.588	0.900	2.89	14.6	14.6	14.0	1.22	NONE	1.40	86	1.41	93	1.41	104	1.75	NONE
1477	547.5	4.610	0.896	2.99	14.2	14.3	14.1	1.22	NONE	1.40	86	1.42	92	1.41	103	0.87	NONE
1478	546.0	4.608	0.896	2.99	14.4	14.4	13.8	1.22	NONE	1.41	86	1.42	93	1.42	103	1.75	NONE
1480	542.3	4.610	0.893	2.89	14.3	14.1	13.5	1.22	NONE	1.41	86	1.41	93	1.42	103	1.75	NONE






FIGURE 1



CHARACTERISTIC 2-HOUR RATE DISCHARGE CURVES

GULTON 12 AMPERE-HOUR NICKEL CADMIUM SEALED CELLS

FIGURE 2



CHARACTERISTIC 48-HOUR OVERCHARGE CURVES
GULTON 12 AMPERE-HOUR NICKEL CADMIUM SEALED CELLS

FIGURE 3

DISTRIBUTION LIST

COPY NO.

- 1-4 National Aeronautics and Space Administration, Goddard Space Flight Center (Mr. Thomas Hennigan, Code 636), Greenbelt, Maryland 20771
- 5 National Aeronautics and Space Administration, Goddard Space Flight Center (Mr. Joseph Sherfey, Code 652), Greenbelt, Maryland 20771
- 6 National Aeronautics and Space Administration, Goddard Space Flight Center (Mr. W. I. Gould, Code 621), Greenbelt, Maryland 20771
- 7 National Aeronautics and Space Administration (Mr. Ernst M. Cohn, Code RNW), Washington, D. C. 20546
- 8 National Aeronautics and Space Administration (Mr. James R. Miles, Code SL), Washington, D. C. 20546
- 9 National Aeronautics and Space Administration (Mr. A. M. Andrus, Code ST), Washington, D. C. 20546
- 10 National Aeronautics and Space Administration (Mr. Arvin Smith, Code RNW), Washington, D. C. 20546
- 11 National Aeronautics and Space Administration, Goddard Space Flight Center (Office of the Director), Greenbelt, Maryland 20771
- 12-14 National Aeronautics and Space Administration, Goddard Space Flight Center (Office of Assistant Director, Space Science and Satellite Applications), Greenbelt, Maryland 20771
- 15-17 National Aeronautics and Space Administration, Goddard Space Flight Center (Office of Assistant Director, Tracking and Data Systems), Greenbelt, Maryland 20771
- 18-20 National Aeronautics and Space Administration, Goddard Space Flight Center (Office of Technical Services), Greenbelt, Maryland 20771
- 21-22 National Aeronautics and Space Administration, Goddard Space Flight Center (GSFC Library), Greenbelt, Maryland 20771
- 23 National Aeronautics and Space Administration, Goddard Space Flight Center (Contracting Officer, Code 246), Greenbelt, Maryland 20771

- 24-27 National Aeronautics and Space Administration, Goddard Space Flight Center (Technical Information Division, Code 250), Greenbelt, Maryland 20771
- 28-30 National Aeronautics and Space Administration, Scientific and Technical Information Facility, P. O. Box 5700, Bethesda, Maryland 20014
- 31 National Aeronautics and Space Administration, Ames Research Center (Mr. A. S. Hertzog/Mr. J. R. Swain), Moffett Field, California 94035
- 32 National Aeronautics and Space Administration, Langley Research Center (Mr. S. T. Peterson/Mr. Harry Ricker), Langley Station, Hampton, Virginia 23365
- 33 National Aeronautics and Space Administration, Lewis Research Center (Mr. Robert Miller), 21000 Brookpark Road, Cleveland, Ohio 44135
- 34 National Aeronautics and Space Administration, Lewis Research Center (Mr. N. D. Sanders), 21000 Brookpark Road, Cleveland, Ohio 44135
- 35 National Aeronautics and Space Administration, Lewis Research Center (Mr. Robert L. Cummings), 21000 Brookpark Road, Cleveland, Ohio 44135
- 36 National Aeronautics and Space Administration, Manned Space Craft Center (Mr. Richard Ferguson for EP-5), Houston, Texas 77058
- 37 National Aeronautics and Space Administration, Manned Space Craft Center (Mr. Robert Cohen), Houston, Texas 77058
- 38 National Aeronautics and Space Administration, Manned Space Craft Center (Mr. James T. Kennedy), Houston, Texas 77058
- 39 National Aeronautics and Space Administration, Manned Space Craft Center (Mr. Forrest E. Eastman, EE-4), Houston, Texas 77058
- 40 National Aeronautics and Space Administration, Marshall Space Flight Center (Mr. Philip Youngblood), Huntsville, Alabama 35812
- 41 Jet Propulsion Laboratory (Mr. Aiji Uchiyama), 4800 Oak Grove Drive, Pasadena, California 91103

- 42 U. S. Army Engineer R & D Labs. (Electrical Power Branch),
Fort Belvoir, Virginia 22060
- 43 U. S. Army Engineer R & D Labs. (Mr. Arthur F. Daniel, Code
SELRA/SL-PS), Fort Monmouth, New Jersey 07703
- 44 U. S. Army Materiel Command, Harry Diamond Labs. (Mr. Nathan
Kaplan), Room 300, Building 92, Connecticut Avenue & Van Ness
Street, N.W., Washington, D. C. 20438
- 45 U. S. Army Materiel Command, Research Division (Mr. John W.
Crellin), AMCRD-RSCM T-7, Washington 25, D. C.
- 46 Natick Labs., Clothing & Organic Materials Division (Mr. Leo A.
Spano/Mr. Robert N. Walsh), Natick, Massachusetts
- 47 U. S. Army TRECOM, Physical Sciences Group (SMOFE), Ft. Eustice,
Virginia 23604
- 48 U. S. Army Research Office (Mr. Paul Greer/Dr. Wilhelm
Jorgensen), Box CM, Duke Station, Durham, North Carolina
- 49 U. S. Army Mobility Command, Research Division (Mr. O. Renius,
AMSMO-RR), Center Line, Michigan 48015
- 50 Headquarters, U. S. Army Materiel Command, Development
Division (Mr. Marshall D. Aiken, AMCRD-DE-MO-P),
Washington 25, D. C.
- 51 Office of Naval Research (Dr. Ralph Roberts/Mr. H. W. Fox)
Department of the Navy, Washington 25, D. C.
- 52 Chief, Bureau of Naval Weapons (RAAE), Navy Department,
Washington, D. C. 20360
- 53 Chief, Bureau of Ships (Mr. Bernard B. Rosenbaum, Code 340/
Mr. C. F. Viglotti, Code 660), Navy Department,
Washington, D. C.
- 54 Commanding Officer, U. S. Naval Ordnance Laboratory
(Mr. William C. Spindler, Code 441), Corona, California 91720
- 55 Commander, U. S. Naval Ordnance Laboratory White Oak
(Mr. Philip B. Cole, Code WB), Silver Spring, Maryland 20919
- 56 U. S. Naval Research Laboratory (Code 6160),
Washington, D. C. 20390

- 57 Wright-Patterson Air Force Base, Aeronautical Systems Division
(Mr. James Elsworth Cooper), Dayton, Ohio 45433
- 58 AF Cambridge Lab. (Mr. F. X. Doherty/Mr. Edward Raskind),
L. G. Hanscom Field, Bedford, Massachusetts 01731
- 59 Rome Air Development Center, ESD (Mr. F. J. Mollura),
Griffiss Air Force Base, New York 13442
- 60 CAPT William H. Ritchie, Space Systems Division (SSZAE-11),
Air Force Unit Post Office, Los Angeles, California 90045
- 61 CAPT William Hoover, Air Force Ballistic Missile Division
(WEZYA-21), Air Force Unit Post Office, Los Angeles,
California 90045
- 62 Office of the Deputy Commander AFSC for Aerospace Systems
(Mr. W. J. Bennison), United States Air Force, Los Angeles,
California 90045
- 63 U. S. Atomic Energy Commission, Army Reactors, DRD,
(Mr. Donald B. Hoatson), Washington, D. C. 20545
- 64 Institute for Defense Analyses (Dr. G. Szego/Mr. R. Hamilton),
400 Army-Navy Drive, Arlington, Virginia 22202
- 65 National Bureau of Standards (Dr. W. J. Hamer),
Washington 25, D. C.
- 66 Power Information Center, University of Pennsylvania, Moore
School Building, 200 South 33rd Street, Philadelphia,
Pennsylvania 19104
- 67 Office of Technical Services, Department of Commerce,
Washington, D. C. 20009
- 68 Mr. R. A. Eades, D.R.S., British Embassy, 3100 Massachusetts
Avenue, N.W., Washington, D. C. 20008
- 69 Canadian Joint Staff, Defense Research Member (WASA),
2450 Massachusetts Avenue, N.W., Washington 25, D. C.
- 70-75 Gulton Industries, Alkaline Battery Division (Dr. Robert Shair),
Metuchen, New Jersey 08840